

27, SAMARPAN BUNGLOWS, NR. JUDGES BUNGLOWS CROSS ROAD, BODAKDEV, AHMEDABAD-15. INDIA. info@sunlanchemicals.com sunlanchemicals@com

# **UV INKS & VARNISHES** TECHNICAL DATA SHEET



: UV0909 - GLOSS TRP INK FOR PAPER **PRODUCT** 

**BRAND** : SUNLAN CHEMICALS

CLASSIFICATION: UV INKS

**PACKAGING** 

**COLOR** : REFER TO COLOR SAMPLE

#### **SUBSTRATES:**

Uv0909 - GLOSS TRP INK For Paper

## **FINISHED PRODUCT**

PC, PVC, copperplate paper, card paper, synthetical paper and other package printing paper.

### **PRODUCT CHARACTER:**

High gloss, good flow capability, high durability and good chemical resistance.







Anti-Broken



Good Adhesion



Environmental

G	I	O	S	S

**Product** UV0909 UV1827

Good Flexibility Glossiness

95-98

88-90

**Anti-Water** Grade5 Grade5

**Solvent Resistance** Grade5

Grade3

**Flexibility** Average

**Adhesion** Good

**TECHNICAL PARAMETER:** 

**Product** UV0909

**Appearance** Milk white UV1827 Milk white

Viscosity/25? 65-90 90-110

**Curing-speed** 20-30m/min 15-25m/min

**Curing-Power** 70mj/cm2 110mj/cm2

Average

Resin ≥98.5% ≥99%

Grade3

#### **APPLICATION INFORMATION:**

MESH: Monofilament mesh, 300-350 mesh with 13-15 N/cm<sup>2</sup>.

SQUEEGEE: 65-75 durometer solvent resistance blade, such as PU.

**COVERAGE:** Depends on the printing situation.

UV MACHINE: 5KW UV lamp 2pcs.

THINNER: UV009 thinner(reduce the viscosity).

**CLEAN UP: DG001** 

#### NOTE:

- 1. Please test before printing.
- 2. Please noted that UV0909 / UV1827, the character of anti-broken and anti-press is not good for some paper.
- 3. UV3636/ UV3645 is better than UV0909 / UV1827 about the flexibility and adhesion. Noted the after-tack under high temp. Please note the nice printing environment and stack after full dry.

## PRODUCT PACKAGE:

1kg/5kgs/20kgs.

## SOTRAGE:

12 months with 5-25°C, far away from strong light, strong acid and strong super salinity.